



1 PRODUCT NAME

THERMAX Metal Building Board

2 Manufacturer

The Dow Chemical Company
 Building Materials
 200 Larkin
 Midland, MI 48674
 1-866-583-BLUE (2583)
 Fax 1-989-832-1465
 www.dowstyrofoam.com/architect

3 Product Description

THERMAX* Metal Building Board consists of a polyisocyanurate foam core with 1.25 mil embossed aluminum foil facers on both sides. In a standing seam roof, the embossed facers help dampen the noise resulting from the system's movement when outside temperatures change. THERMAX Metal Building Board has a Sound Transmission Classification (STC) of 15. And, it can be installed exposed to the interior without a thermal barrier.

BASIC USE

THERMAX Metal Building Board provides both insulation value and an interior finish system for walls in metal buildings. The boards also find application in standing seam metal roofs (SSRs). THERMAX Metal Building Board is listed in 1, 2, 3 and 4 hour UL fire rated wall assemblies.

SIZES

Width and length:
 4' x 8', 4' x 10'
 Edge treatments:
 Square edge, shiplap

Product thicknesses and R-values are shown in Table 1. Not all products are available in all parts of the country. Additional product sizes are available by custom order. Consult a Dow representative about other sizes and lead-time requirements.

4 Technical Data

APPLICABLE STANDARDS

THERMAX Metal Building Board meets ASTM C1289-02 – Standard Specification for Faced Rigid Cellular Polyisocyanurate Thermal Insulation Board, Type I, Class 2 (previously known as Federal Specification HH-I-1972), which includes:

- ASTM C203 – Standard Test Methods for Breaking Load and Flexural Properties of Block-Type Thermal Insulation
- ASTM C209 – Standard Test Methods for Cellulosic Fiber Insulating Board
- ASTM C518 – Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- ASTM D1621 – Standard Test Method for Compressive Properties of Rigid Cellular Plastics
- ASTM D2126 – Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging
- ASTM E96 – Standard Test Method for Water Vapor Transmission of Materials
- ASTM D1623 – Standard Test Method for Tensile and Tensile Adhesion Properties of Rigid Cellular Plastics

TABLE 1

THERMAX Metal Building Board R-Values	
Nominal Foam Thickness, in.	Stabilized R-Value ^(1, 2)
0.5	3.3
0.75	5.0
1.0	6.5
1.25	8.0
1.55	10.0
1.75	11.4
2.0	13.0
2.5	15.8
3.0	19.0
3.5	22.1
4.0	25.3

(1) R means resistance to heat flow. The higher the R-value, the greater the insulating power. Stabilized R-values @ 75°F mean temperature determined in accordance with ASTM C518.
 (2) R-values expressed in ft²•h•°F/Btu.

THERMAX Metal Building Board

TABLE 2

Physical Properties of THERMAX Metal Building Board	
Property and Test Method	Value
Compressive Strength ⁽¹⁾ , ASTM D1621, psi, min.	25.0
Flexural Strength, ASTM C203, psi, min.	40.0
Dimensional Stability, ASTM D2126, % linear change, max.	0.5
Water Absorption, ASTM C209, % by volume, max.	0.3
Water Vapor Permeance, ASTM E96, perms, max.	<0.03
Maximum Use Temperature, °F	250

(1) Vertical compressive strength is measured at 10 percent deformation or at yield, whichever occurs first.

PHYSICAL/CHEMICAL PROPERTIES

THERMAX Metal Building Board exhibits the properties and characteristics indicated in Table 2 when tested as represented.

For chemical resistance properties of THERMAX Metal Building Board, see Table 3.

ENVIRONMENTAL DATA

THERMAX Metal Building Board is manufactured with hydrocarbon blowing agents, which have no ozone depletion potential.

FIRE PROTECTION

THERMAX products should be used only in strict accordance with product application instructions. THERMAX products, when used in a building containing combustible materials, may contribute to the spread of fire. For more information, consult MSDS and/or call Dow at 1-866-583- BLUE (2583). In an emergency, call 1-989-636-4400.

CODE COMPLIANCES

THERMAX Metal Building Board complies with the following codes:

- International Residential Code 2003 (IRC) Section 314
- International Building Code (IBC) Section 2603
- National Evaluation Services (NES) NER-681
 - BOCA – Section 2603.0 and Research Report #98-25 (replaced)
 - ICBO – Section 2602 and Evaluation Report #3223 (replaced)
 - SBCCI – Section 2603 and Evaluation Report 9574C (replaced)
- FM 4880 – Wall-Ceiling Construction Metal-Faced – Class 1 Fire Rated to Max. 30' High, 4.25" Thick, 4' Wide, When Installed as Described in the Current Edition of FMRC Approval Guide
- THERMAX products are covered under Underwriters Laboratories Inc. (UL) files R5622, R8181 and R2637
- UL 1256 – Fire Test of Roof Deck Constructions, Roof Deck Construction No. 120 and No. 123
- UL 723 (ASTM E84) Surface Burning Characteristics of Building Materials
- The following designs are 1, 2, 3 or 4 hour wall rated assemblies as listed in the UL Fire Resistance Directory: U026, U324, U325, U326, U330, U354, U355, U460, U902, U904, U905, U906, U907

TABLE 3

Chemical Resistance of THERMAX Metal Building Board	
Acid, inorganic	Not recommended
Acid, organic	Excellent
Alcohol	Excellent
Asphalt, water-based	Good
Bases (caustics)	Poor
Brines and other salts	Excellent
Cements and mortar	Poor
Gases, carbon dioxide (CO ₂)	Excellent
Gasoline	Excellent
Hydrocarbons	Excellent
Insecticides	Excellent
Kerosene	Excellent
Mineral oil USP	Excellent
Naphtha	Excellent
Paints, alcohol-based	Excellent
Paints, water-based	Excellent
Polyglycols, including propylene glycol	Excellent
Water ⁽¹⁾	Excellent

(1) Water may cause discoloration of aluminum facers. This does not impact the R-value of dry, core insulation. NOTE: This table should be used as a guide only. For design purposes, specific test data on the intended application may be needed.

- Fire Performance Evaluation of an Exterior Masonry Wall System Incorporating THERMAX Insulation Tested in Accordance With NFPA 285, 1998 Edition (UBC 26.9, intermediate scale – multistory testing)
- FMVSS No. 302 – Flammability of Interior Materials – Passenger Cars, Multipurpose Passenger Vehicles, Trucks and Buses (Docket No. 3-3; Notice 4)
- Miami-Dade NOA 02-0703.02 Interior Insulation on CMU Block
- Miami-Dade NOA 02-0703.03 Insulated Wall
- Miami-Dade NOA 02-0703.05 Insulated Roof Assembly

Contact your Dow sales representative or local authorities for state and local building code requirements and related acceptances.

5 Installation

THERMAX Metal Building Boards are lightweight and can be sawed or cut with a knife. They install quickly to walls and ceilings – inside and outside of purlins, trusses or bar joints. Butt joints must be installed over structural members. The surface of the insulation at all joints must be continuously sealed with tape or with one of Dow's joint closure systems.

Contact a local Dow representative or access the literature library at www.dowstyrofoam.com/architect for more specific instructions.

6 Availability

THERMAX Metal Building Board is manufactured in several locations and is distributed through an extensive network of manufacturers and distributors. For more information, consult the nearest Dow sales office or call 1-800-232-2436.

7 Warranty

Fifteen-year limited thermal warranty.

8 Maintenance

Not applicable.

9 Technical Services

Dow can provide technical information to help address questions when using THERMAX Metal Building Board. Technical personnel are available to assist with any insulation project. Call 1-866-583-BLUE (2583).

10 Filing Systems

- www.dowstyrofoam.com/architect
- www.sweets.com

IN THE U.S.:

- For Technical Information: **1-866-583-BLUE (2583)**
- For Sales Information: **1-800-232-2436**

THE DOW CHEMICAL COMPANY

- Building Materials • 200 Larkin • Midland, MI 48674 • www.dowstyrofoam.com/architect

NOTICE: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

COMBUSTIBLE: THERMAX products should be used only in strict accordance with product application instructions. THERMAX products, when used in a building containing combustible materials, may contribute to the spread of fire. For more information, consult MSDS and/or call Dow at 1-866-583-BLUE (2583). In an emergency, call 1-989-636-4400.

WARNING: THERMAX insulation does not constitute a working walkable surface or qualify as a fall protection product.



Living.
Improved daily.

