

## WMP-10 BLACK

BLACK COATING / POLYPROPYLENE / SCRIM / KRAFT

Meets ASTM C1136, Type II, IV

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
Black Coating	Flame Resistant	0.0002 inch	5.1 micron
Film	Metallized Polypropylene	0.0015 inch	38.1 micron
Adhesive	Flame Resistant		
Reinforcing	Tri-directional	5 / inch (MD)	20 / 100 mm (MD)
	Fiberglass/Polyester	5 / inch (XD)	20 / 100 mm (XD)
Kraft	White	14 lbs / 3000 ft <sup>2</sup>	23 g / m <sup>2</sup>

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	21 lbs / 1000 ft <sup>2</sup>	103 g / m <sup>2</sup>
Permeance (WVTR)	ASTM E96 Procedure A	0.02 perm (grains/hrft <sup>2</sup> in Hg)	1.15 ng / N's
Bursting Strength	ASTM D774	65 psi	4.6 kg / cm <sup>2</sup>
Puncture Resistance	ASTM C1136	125 beach units	3.7 Joules
Tensile Strength	ASTM C1136	40 lbs/inch width (MD)	7.0 kN / m (MD)
		35 lbs/inch width (XD)	6.1 kN / m (XD)
Caliper / Thickness	Micrometer	0.009 inch	229 micron
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion	No Corrosion
		No Delamination	No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible	Remains Flexible
		No Delamination	No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible	Remains Flexible
		No Delamination	No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665 / C1338	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%

FIRE TESTING	UL-723 / ASTM E84	
	Flame Spread	Smoke Developed
Film Exposed	10	10
Kraft Exposed	15	5

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION

Lamtec Corporation Bartley-Chester Road P.O. Box 37 Flanders, New Jersey 07836-0037 USA

Phone: (973) 584-5500  
(800) 852-6832

[www.lamtec.com](http://www.lamtec.com)

Fax: (973) 584-5178  
(888) 852-6832